



K-Sentials

IC025.de

Thermal anhydrite

2017-11

Thermal anhydrite

FGD gypsum based crystallized water-free calcinated thermal anhydrite

Product description

FGD gypsum based crystallized water-free calcinated thermal anhydrite for use in the manufacture of calcium sulphate screed as a binder and filler in industrial applications.

Order information	Material no.
Bulk	5442
Big Bag	127866
Bag 25kg	429187

Technical data	Unit	Value
Oversize material	%	
90 µm		< 3
63 µm		< 10
Purity	%	> 90
Bulk density (dry) approx.	g/l	1050 – 1250

All values are reference values. They are subject to divergences and can deviate in individual cases from the stated ranges.

Knauf Direkt
Technical Advisory Service:

▶ knauf-direkt@knauf.de
▶ www.k-sentials.de

Knauf Gips KG Am Bahnhof 7, 97346 Iphofen, Germany

All technical changes reserved. Only the current printed instructions are valid. The stated information represents current state-of-the-art Knauf technology. The entire state of approved engineering rules, appropriate standards, guidelines, and rules of craftsmanship are not included herewith. These and all application instructions have to be adhered to separately by the installer. Our warranty is expressly limited to our products in flawless condition. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas.
All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require our expressed permission..

All given data are reference values with tolerance due to source and production.
Determination method according to Knauf test procedure, can be asked for, if required.

K | SENTIALS